



HIGH-P WATER SHED

MOISTURE MANAGEMENT BUILDING WRAP

| WaterShed™ | | Limited 10 Year Warranty | |
|---|--------------------------------|--------------------------|-----------------------------|
| TEST | PRODUCT SPECIFICATIONS | | TEST METHOD |
| Composition | Non - Woven Film with CLAF® | | |
| Weight | 2.2 oz/yd2 (+/-5%) | | TAPPI T-410 |
| Thickness | Avg. 8.0 mils | | ASTM D3776 |
| Tensile Strength | MD 45 LB | CD 45 LB | ASTM D5034 |
| Water Penetration | > 300 cm | | AATCC 127 |
| Trapezoidal Tear | MD 13.5 LB | CD 12.5 LB | ASTM D1117 |
| Air Permeance | 0.00082 (cfm/ft2 @ 1.57 psf) | | ASTM E 2178 |
| MTVR/Perms | 55 Perms | | ASTM E 96-05 Method A |
| UV Resistance | 120 Days | | |
| Drainage Efficiency | >95% | | ASTM E2273* |
| Fire Rating | Class A - 5 Flame Spread | | ASTM E 84 |
| | Class A - 45 Smoke Development | | ASTM E 84 |
| Roll Sizes Other Sizes Available | WIDTH | | LENGTH (ROLLS/PALLET) |
| | 9' | | 100'(72), 150'(50), 195(40) |
| | 10' | | 100'(72), 150'(50), 195(40) |

*ICC-ES AC 235 Section 4.5

WaterShed™ High-P:

FOR USE AS A REPLACEMENT FOR GRADE D PAPER AS A MOISTURE, AIR INFILTRATION BARRIER, AND DRAINAGE WRAP

Meets the following certifications: Complies with ICC-ES AC38 "Water Resistive Barriers/Weather Barriers"

ICC report No. ESR-4665

Disclaimer: The information presented herein has been compiled from sources considered to be accurate and reliable but is not guaranteed to be so. In practice, the differences in materials, substrates, storage conditions, actual site conditions and other factors outside of Perma "R" Products' control are such that Perma "R" Products assumes no liability, nor makes any warranty, express or implied for such information, recommendations or instructions related to its products. It is the users responsibility to determine the suitability of any material for specific purpose and to adopt such safety precautions as may be necessary.

2604 SUNSET DR. GRENADA, MS 38901

1-800-647-6130

WWW.PERMARPRODUCTS.COM

