



TECHNICAL DATA SHEET

WaterShed™		Limited 10 Year Warranty	
TEST	PRODUCT SPECIFICATIONS		TEST METHOD
Composition	Non - Woven Film with CLAF®		
Weight	2.2 oz/yd2 (+/-5%)		TAPPI T-410
Thickness	Avg. 8.0 mils		ASTM D3776
Tensile Strength	MD 45 LB	CD 45 LB	ASTM D5034
Water Penetration	> 300 cm		AATCC 127
Trapezodial Tear	MD 13.5 LB	CD 12.5 LB	ASTM D1117
Air Permeance	0.00082 (cfm/ft2 @ 1.57 psf)		ASTM E 2178
MTVR/Perms	55 Perms		ASTM E 96-05 Method A
UV Resistance	180 Days		
Drainage Efficiency	>95%		ASTM E2273*
Fire Rating	Class A - 5 Flame Spread		ASTM E 84
	Class A - 45 Smoke Development		ASTM E 84
Roll Sizes	WIDTH	LENGTH (ROLLS/PALLET)	
Other Sizes Available	9'	100'(72), 150'(50), 195(40)	
	10'	100'(72), 150'(50), 195(40)	

*ICC-ES AC 235 Section 4.5

WaterShed™ High-P:

FOR USE AS A REPLACEMENT FOR GRADE D PAPER AS A MOISTURE, AIR INFILTRATION BARRIER, AND DRAINAGE WRAP

Meets the following certifications: Complies with ICC-ES AC308 "Water Resistive Barriers/Weather Barriers"

ICC report No. ESR-4665

Disclaimer: The information presented herein has been compiled from sources considered to be accurate and reliable but is not guaranteed to be so. In practice, the differences in materials, substrates, storage conditions, actual site conditions and other factors outside of Perma "R" Products' control are such that Perma "R" Products assumes no liability, nor makes any warranty, express or implied for such information, recommendations or instructions related to its products. It is the users responsibility to determine the suitability of any material for specific purpose and to adopt such safety precautions as may be necessary.

2604 SUNSET DR. GRENADA, MS 38901

1-800-647-6130

WWW.PERMARPRODUCTS.COM

